

# UV PRO 550

## PRODUCT TYPE

UV PRO 550 is a 100% solids, Ultraviolet-Light curable Anti-Fog formulated to provide resistance to fogging on polycarbonate and other plastics.

## PROPERTIES

- Permanent, Moisture absorbing resistance to fogging
- Adhesion to a variety of plastics types including polycarbonate
- Passes Fog and Abrasion resistance requirements of EN 166/168
- Primerless

## SAFETY AND EXPOSURE

All users must read and understand the Safety Data Sheet prior to using this product.



## LIQUID PROPERTIES at 25°C

PROPERTY	RANGE
Viscosity	200 – 300 centipoise (cP)
Specific Gravity	1.01 – 1.03
Solids, % by weight	100
Compatible Solvents	Alcohols (butanol)
Maximum Dilution	50%

## CURED COATING CHARACTERISTICS

Polycarbonate substrate, 10.0 microns

PROPERTY	RANGE				
Light Transmittance	≥ 88% (polycarbonate); ≥ 98% (glass)				
Haze	< 1.0%				
Adhesion	100% (5B)				
Thickness, microns	6 – 18 (10)				
Chemical Resistance	<table border="0"> <tr> <td style="text-align: right; vertical-align: top;">Pass</td> <td>Alcohols (ethanol/isopropanol), typical household cleaners, aliphatic/fuels (diesel/ gasoline / heptane / cyclohexane), Dilute alkali and acids</td> </tr> <tr> <td style="text-align: right; vertical-align: top;">Fail</td> <td>Esters (ethyl acetate), Ketones (acetone, 2-heptanone;2-butanone),Dichloromethane, Concentrated acids and alkali</td> </tr> </table>	Pass	Alcohols (ethanol/isopropanol), typical household cleaners, aliphatic/fuels (diesel/ gasoline / heptane / cyclohexane), Dilute alkali and acids	Fail	Esters (ethyl acetate), Ketones (acetone, 2-heptanone;2-butanone),Dichloromethane, Concentrated acids and alkali
Pass	Alcohols (ethanol/isopropanol), typical household cleaners, aliphatic/fuels (diesel/ gasoline / heptane / cyclohexane), Dilute alkali and acids				
Fail	Esters (ethyl acetate), Ketones (acetone, 2-heptanone;2-butanone),Dichloromethane, Concentrated acids and alkali				

## WARRANTY LIMITATIONS

The physical and performance properties cited herein represent typical values for UV PRO 550 Coating, and are not meant as exact specifications. Customers must conduct their own validation testing to determine the appropriate use of this product for any purpose. This information is not to be considered a warranty or license to infringe upon any patented process or product; no liability for infringement arising out of such a use is assumed.

## DELIVERY OPTIONS

The UV PRO 550 Coating liquid is available for shipment within two weeks of order confirmation, and is available in quart, gallon, and five-gallon pail containers. Contact Exxene to select the best payment option and the optimum shipping method according to your preference and region. All charges, duties, and fees associated with the shipment and its contents are the responsibility of the customer.

## APPLICATION PARAMETERS

PROPERTY	RANGE
Application Methods Dip Spray Flow Coat	1 – 3.0 mm /second withdrawal rate 20 – 45 psi HVLP; fine tip As appropriate to flow system
Environment Temperature / Humidity	16 – 30°C / 20 – 65 % RH
Air quality	Laminar, top-down flow < 5 cfm Particle count as appropriate ( ≤ Class 10,000 )
Coating Temperature	Within 5° of Ambient temperature
Coating Filtration	Polyethylene or polypropylene; nominal media rated at 0.5 to 1.0 microns as a pre-filter; absolute media rated at 5.0 to 10.0 microns. <i>Filter all coating before use.</i>
Cure Conditions	< 2 seconds using Medium pressure Mercury vapor lamp

## EQUIPMENT PREPARATION

**Compatible Materials:** All equipment surfaces must be constructed of stainless steel, polyethylene, polypropylene or similar, chemical resistance substances. Mild steel, brass, copper, and polyvinyl chloride (PVC) or plasticizer-containing materials cannot be allowed to contact the coating liquid. Solvents other than those used to dilute the coating liquid are not allowed to contact the coating liquid.

**Cleaning:** All coating equipment must be thoroughly cleaned with a compatible solvent to remove all traces of other coatings, solvents, or old batches of the same product. After all residues have been removed from the equipment, multiple rinses of butanol followed by thorough drying are used to prepare the system for the introduction of filtered UV PRO 550 Coating liquid.

**STORAGE** UV PRO 550 liquid is stored at room temperature, or at refrigerated temperatures above 5 °C. Do not freeze. When stored in the original, sealed container, the liquid should be used within six months of the production date.

**SUPPORT** Contact Us via telephone at +1(361)991-8391, email [Info@Exxene.com](mailto:Info@Exxene.com), or fax to +1(361)991-9057. We are located at 5939 Holly Road, Corpus Christi, TX 78414.